



黑天目



1201 deg.C



C. 6

RECIPE

P3296-A Potash Feldspar	49.31
P3309 China Clay	2.28
P3345-A Talc (theoretical)	0.16
P3346-A Calcium Carbonate	24.00
P3337-C Quartz	24.26

COLOURANTS ETC.

P3410 Red Iron Oxide	2.00
P3402 Cobalt Carbonate	0.50
P3415 Manganese Dioxide	1.00

Seger. % Anal.

Al : Si	9.7425
Coef.of Exp.	11.0925
Surf.Tens.	360.124
Clay Body	
Colour	
Glaze Type	Tenmoku
Opacity	Opaque
Texture	Glossy
Stability	
Fit	



	Seger	% Anal.
KNO	0.2689	9.37%
CaO	0.7281	15.11%
MgO	0.0031	0.05%
BaO		
ZnO		
PbO		
Li2O		
SrO		
Al2O3	0.2967	11.19%
P2O5		
B2O3		
SiO2	2.8903	64.28%
TiO2		
ZrO2		
K2O	0.2689	9.37%
Na2O		

Comment

改自 a的黑天目，物資不變，只將溫度調低。

Date Last Change12/5/2004

