



Oxidation

Date:15/6/2004

小慧提供透明釉



小慧提供透明釉 c



1285 deg.C



C. 10

RECIPE

Cornish Stone	52.00
Albany Slip Clay	20.00
Quartz	13.00
Strontium Carbonate	9.00
Colemanite	6.00

COLOURANTS ETC.

Al : Si	9.9138
Coef.of Exp.	7.9767
Surf.Tens.	352.018
Clay Body	
Colour	
Glaze Type	Clear
Opacity	Clear
Texture	Glossy
Stability	
Fit	

Seger. % Anal.

	Seger	% Anal.
KNO	0.3060	5.32%
CaO	0.3360	4.31%
MgO	0.0720	0.66%
BaO		
ZnO		
PbO		
Li2O		
SrO	0.2860	6.78%
<b>Al2O3</b>	<b>0.4990</b>	<b>11.63%</b>
P2O5		
B2O3	0.1960	3.12%
<b>SiO2</b>	<b>4.9470</b>	<b>68.01%</b>
TiO2	0.0090	0.16%
ZrO2		
K2O	0.1330	2.87%
Na2O	0.1730	2.45%

Comment

No Albany Slip Clay.  
Could not try this recipe.  
And the temp is too high for us.

Date Last Change 29/4/2004

